



## DuPont™ Window & Door Premier Silicone

- Water ready in 2 hours
- Waterproof & crackproof
- Weatherproof seal
- Lifetime durability
- Low VOC – low odor
- Mineral spirit clean up

Packaging	Color	Part#	UPC#	I2of5
9.8 fl oz. (290 mL)	White	07600	843034076005	10843034076002
2.8 fl oz. (162 mL)	White	07601	843034076012	10843034076019
9.8 fl oz. (290 mL)	Clear	07602	843034076029	10843034076026
2.8 fl oz. (162 mL)	Clear	07603	843034076036	10843034076033
9.8 fl oz. (290 mL)	Almond	07604	843034076043	10843034076040
9.8 fl oz. (290 mL)	Black	07605	843034076050	10843034076057
9.8 fl oz. (290 mL)	Bronze	07606	843034076067	10843034076057
9.8 fl oz. (290 mL)	Brown	07607	843034076074	10843034076071
9.8 fl oz. (290 mL)	Cedarwood	07608	843034076081	10843034076088
9.8 fl oz. (290 mL)	Light Gray	07610	843034076104	10843034076101

### Company Information:

**Supplied by:** Tower Sealants, 2095 Memorial Park Rd., Gainesville, GA 30504  
**Customer Service:** 866-897-7568  
**Fax Number:** 866-897-7569  
**Website:** [www.towersealants.com](http://www.towersealants.com)

DuPont™ Window & Door Premier Silicone is a premium 100% silicone rubber sealant that is ideal for sealing cracks and gaps around windows, doors, plumbing openings, vents and ducts. It provides a watertight, flexible seal that is resistant to sunlight, rain, snow, and extreme temperatures. Cured bead will not crack, crumble or shrink and adheres to most wood, metal, vinyl siding, drywall/plaster, glass and painted surfaces. It is designed to be used on windows, doors, siding, trim, gutters and molding. Once applied, DuPont™ Window & Door Premier Silicone can be exposed to water in 2 hours. Once cured, the sealant is unaffected by temperature extremes (-60°F to 400°F) and is mold and mildew resistant. Not for use on Tyvek®. For Tyvek® installation use DuPont™ Residential Sealant.

### Suggested Uses:

#### Caulks and seals cracks, joints and seams around the following:

- Windows and Doors
- Siding and Trim
- Plumbing openings
- Vents
- Ducts
- Molding

#### Substrates include, but not limited to:

- Wood
- Metal
- Vinyl siding
- Glass
- Painted surfaces
- Drywall/plaster

## Performance Characteristics:

- Meets ASTM Specification C-920, Type-S, Grade NS, Class 25, use NT, M, G, A & O.
- Meets Fed. Spec. TT-S-00230C and TT-S-001543A.

## Application:

- Clean surface to be caulked.
- For gaps greater than 1/2" deep, use a backer rod.
- Insert caulk tube into the caulk gun.
- Cut the dispensing nozzle at a 45° angle.
- Puncture inner foil seal
- While slowly squeezing the caulk gun trigger, gently push the sealant nozzle along the gap to be sealed. Ensure complete contact is made on both surfaces being sealed.
- Smooth applied bead with a moist cloth or finishing tool.
- Clean tools with mineral spirits
- Cured bead should be between 1/8" and 1/2" wide.
- Allow 2 hours curing time before exposing to a wet or damp environment.
- Coverage: 53 linear feet for a 3/16" bead (9.8 oz cartridge) and 15 linear feet for a 3/16" bead (2.8 oz squeeze tube).

## Physical & Chemical Characteristics:

<b>Vehicle:</b>	<b>One part, neutral cure silicone</b>
<b>Color:</b>	<b>Various</b>
<b>VOC (CARB Method for Chemically Curing Sealant)</b>	<b>&lt;3.0 wt%</b>
<b>VOC (Excluding water and exempt compounds)</b>	<b>&lt;31 g/L</b>
<b>Density:</b>	<b>1.02 to 1.05 g/cm<sup>3</sup></b>
<b>Service Temperature:</b>	<b>-60° to 400° F</b>
<b>Application Temperature Range:</b>	<b>40° to 100° F</b>
<b>Dynamic Joint Movement:</b>	<b>50% (+/- 25%)</b>
<b>Consistency:</b>	<b>2-15 grams per second (non sag)</b>
<b>Shelf Life:</b>	<b>18 months</b>
<b>Coverage:</b>	<b>53 linear feet with 3/16" bead</b>
<b>Tooling Time:</b>	<b>15 minutes</b>
<b>Skin Forming Time:</b>	<b>30 minutes</b>

## LIMITATIONS:

- NOT INTENDED FOR AREAS THAT WILL BE SUBMERGED IN WATER.
- DO NOT USE ON SURFACES THAT COME IN CONTACT WITH FOOD.
- DO NOT USE IN AQUARIUMS.
- CANNOT BE PAINTED
- KEEP OUT OF REACH OF CHILDREN

## SAFETY:

- See Material Safety Data Sheet for safety information or product label.
- To request a Material Safety Data Sheet call 800-654-0005.